

Amendments to the Claims:

The following listing of claims will replace all prior versions, and listings, of claims in the application:

1. (Currently Amended) A composite material comprising PPTA (poly-p-phenyleneterephthalamide) and nanotubes having an aspect ratio of at least 100 and a cross-sectional diameter of 5 nm or less, the composite material containing up to ~~12~~ 12 wt.% of nanotubes, ~~obtainable by adding the nanotubes to sulfuric acid, decreasing the temperature to solidify the mixture, adding PPTA to the solid mixture, heating to above the solidifying point and mixing the mixture, and spinning, casting, or molding the mixture to the composite material~~ and the composite material having a tensile strength of at least 1.5 GPa and a modulus of at least 50 GPa.

2. (Currently Amended) The composite material of claim 1 wherein the ~~nanotube is a~~ nanotubes are single wall ~~nanotube~~ nanotubes (SWNT).

3. (Previously Presented) The composite material of claim 1 wherein the content of nanotubes is 5 wt.% or less.

4. (Canceled)

5. (Currently Amended) The composite material of ~~claim 4~~ claim 1, wherein the composite material is a fiber.

6. (Withdrawn) A process for making a spin dope solution comprising the steps:

- a) adding nanotubes having an aspect ratio of at least 100 and a cross-sectional diameter of 5 nm or less to sulfuric acid at a temperature above the solidifying point of the sulfuric acid;
- b) decreasing the temperature to below the solidifying point of the sulfuric acid and mixing for a sufficient time to solidify the mixture;

c) adding PPTA to the solid mixture; and

d) heating to above the solidifying point and mixing the mixture.

7. (Withdrawn) The process according to claim 6 wherein in step a) the mixture is mixed for 10 min to 6 h at 10 to 90° C.

8. (Withdrawn) The process according to claim 6 wherein the temperature is decreased in step b) to 7 to -20° C.

9. (Withdrawn) The process according to claim 6 wherein the temperature in step c) is maintained at -5 to 0° C prior to adding PPTA to the mixture.

10. (Withdrawn) The process according to claim 6 wherein the temperature in step d) is elevated to ambient temperature and the mixture is mixed for at least 1 h.

11. (Canceled)

12. (Previously Presented) A fiber having filaments comprising a mixture of PPTA and nanotubes, wherein the fiber is a multifilament fiber comprising at least 5 filaments and the nanotubes have an aspect ratio of at least 100 and a cross-sectional diameter of 5 nm or less.

13. (Withdrawn) The process according to claim 8 wherein the temperature is decreased in step b) to 2 to -12° C.